

EPOLENE® E-16

Low Molecular Weight Polymer

Applications

- Compounding
- Emulsions
- PVC lubrication
- Wax modification

Attributes

- Imparts slip resistances, durability, and toughness to floor finishes
- Oxidized to provide functionality
- Produces stable water based emulsions
- Oxidized low density polyethylene

Product Description

EPOLENE® E-16 is an oxidized low molecular weight polyethylene having properties intermediate between EPOLENE® E-10 polymer and EPOLENE® E-14 polymer. It provides stable, low color emulsions by both atmospheric (wax-to-water) and pressure emulsification methods for such end uses as textiles, floor polishes, inks, and paint rheological additives.

Typical Physical Properties

Property ^a	Test Method b	Typical Value, Units ^c
Acid Number	D-1386	14-18.5 mg-KOH/g
Penetration Hardness	D-5	4 dmm
Mettler Drop Point	D-6090	105 °C
Brookfield Viscosity @ 125 °C	D-4287	550-750 cP
Yellowness Index	E-313	≤ 4.0

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

Packaging

EPOLENE® E-16 is offered in multiple package types. See your Westlake sales or technical representative for packaging offerings and availability.

Storage

The useful life of this product can be affected by storage and handling conditions. This product should be stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures, and contamination. First-in first-out (FIFO) inventory management is recommended.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.